

# SODIUM SILICATE SPECIFICATION

## PAKSIL 25 LR

<i>Ratio</i>	<b>2.40 ± 0.05</b>
<i>Na<sub>2</sub>O%</i>	<b>13.00 - 13.90</b>
<i>SiO<sub>2</sub> %</i>	<b>31.23 - 33.25</b>
<i>Density,@ 20 ° C Baume</i>	<b>51 ± 1</b>
<i>Specific Gravity(G/CM<sup>3</sup>)</i>	<b>1.526 - 1.559</b>
<i>Viscosity (Cps)</i>	-
<i>Grade</i>	<b>Ceramic</b>
<i>Appearance</i>	<b>Hazy</b>

**Deflocculating clays**

**Drilling muds**

**Foundry molds and cores**

**Laminating paper and metal foil**

Date : 07/11/2017

**Suit 9, 5th Floor, NO. 75, Sattari Blvd, Valiasr Str, Tehran, Iran**  
**Tel : +98 21 88192461-2, 88776937, 88776948, Fax : +98 21 88778120**  
**Factory: Kherad Ave., Lia Industrial Zone, Ghazvin, Iran**  
**Tel-Fax : +98 28 33454706-7**