

SODIUM SILICATE SPECIFICATION

PAKSIL 25

<i>Ratio</i>	2.5±0.05
<i>Na₂O%</i>	13.00 - 13.89
<i>SiO₂ %</i>	32.59 - 34.64
<i>Density,@ 20 ° C Baume</i>	52 ± 1
<i>Specific Gravity(G/CM³)</i>	1.543 - 1.576
<i>Viscosity (Cps)</i>	600 - 1500
<i>Grade</i>	Ceramic
<i>Appearance</i>	Hazy

Deflocculating clays

Drilling muds

Foundry molds and cores

Laminating paper and metal foil

Date : 07/11/2017

Suit 9, 5th Floor, NO. 75, Sattari Blvd, Valiasr Str, Tehran, Iran
Tel : +98 21 88192461-2, 88776937, 88776948, Fax : +98 21 88778120
Factory: Kherad Ave., Lia Industrial Zone, Ghazvin, Iran
Tel-Fax : +98 28 33454706-7